

PRODUCT SPECIFICATIONS

FOAM GRADE IDENTIFICATION:		Dri33 Cal 117
1. DENSITY	<u>1.80</u> (lbs/cu ft)	<u>1.60 - 2.40</u> RANGE
2. IFD @25%	<u>33.0</u> (lbs/50 sqin)	<u>28 - 38</u> RANGE
@65%	<u>N/A</u>	
3. SUPPORT FACTOR		<u>N/A</u> MINIMUM
4. HYSTERISIS (% retained)		<u></u> %MINIMUM
5. DYNAMIC FATIGUE IFD LOSS @25%		<u>N/A</u> %MAXIMUM
80k Cycles	HEIGHT LOSS	<u>N/A</u> %MAXIMUM
6. RESILIENCY (ball rebound)		<u>N/A</u> %MINIMUM
7. AIRFLOW		<u>N/A</u> SCFM MINIMUM
8. TENSILE		<u>8</u> PSI MINIMUM
9. TEAR		<u>1</u> PLI MINIMUM
10. ELONGATION (2.5" gauge length)		<u>120</u> % OF ORIGINAL
11. COMPRESSION SET (@90% deflection)		<u>15 @50%</u> %MAXIMUM
12. FILLER CONTENT		<u>0.00</u> %MAXIMUM
13. COLOR		<u>White</u>
14. COMBUSTIBILITY	FMVSS 302	<u>Conforms</u>
	CAL 117 A and D	<u>Conforms</u>
15. OTHER SPECIFICATIONS		
Meets Antibacterial Standard AATCC 147 and/or ISO 20743:2007		
Meets Antifungal Standard AATCC 30		
PPI 20 - 35		

ALL PHYSICAL PROPERTIES TESTING CONFORMS TO ASTM D 3574-08