

Fabric Backed Sew Foam Data Sheet

PROPERTY	TEST METHOD	TYPICAL RESULTS
Density (lbs/cubic ft)	ASTM D3574-05	1.45-1.55
25% IFD (lbs)	ASTM D3574-05	64-76
Tensile Strength (min PSI)	ASTM D3574-05	15
Elongation % (min)	ASTM D3574-05	110
Compression Set @ 75% (max)	ASTM D3574-05	15
Compression Modulus (min)	ASTM D3574-05	1.80
Hysteresis Loss % (max)	ASTM D3574-05	50
Resiliency % (min)	ASTM D3574-05	20
Flammability	CAL TB117-2013	Pass

Note: Results are typical and do not encompass the entire range of values.



Sailrite Enterprises, Inc.
 2390 East 100 South, Columbia City, IN 46725

Phone (800) 348-2769 / (260) 244-4647

Fax (260) 818-2005

Email info@sailrite.com

Sailrite.com

© 2018 Sailrite Enterprises, Inc.