

SEAMARK

**STYLE: MB, MC, MD, ME, MG, MG, MH, MK
ML, MM, MN, MP, MQ, MT, MV, MW, MZ**

<u>PHYSICAL PROPERTIES</u>	<u>TEST METHOD</u>	<u>SPECIFICATION</u>	<u>TYPICAL DATA</u>
WEIGHT:	ASTM D751	477 - 577 g/m ²	528.9 g/m ²
BOND:	ASTM D751	22N/ 51mm MIN.	26N/ 51mm
TENSILE: Warp x Fill	ASTM D751 Grab Method	1000 x 550N MIN.	1238 x 815N
TRAPEZOIDAL TEAR: Warp x Fill	ASTM D1117	140 x 60N MIN.	269 x 111N
STRETCH: Warp x Fill	SAE J855	6.0 x 8.0% MAX.	2.4 x 2.3%
SET: Warp x Fill	SAE J855	3.0 x 3.0% MAX.	1.0 x 0.4%
STIFFNESS: Warp x Fill	ASTM D747	43 x 33 MAX.	19 x 11
WASH SHRINKAGE: Warp x Fill	½ hr. Machine	4.5 x 1.0% MAX.	1.4 x 0.2%
COLD RESISTANCE:	SAE J323B -30°C	Passes	Pass
WATER REPELLENCE:	AATCC TM22	70 rating MIN.	100 rating
XENON WEATHEROMETER RESISTANCE:	SAE J1960 1140 kJ/m ²	Passes	Pass

LAB 220-1
Rev: 2/25/02
Orig: 6/6/94