

## Spun Bonded Polypropylene Non-Woven Material for Masks

TEST		METHOD		UNIT	AVERAGE	MINIMUM
GSM				g/m <sup>2</sup>	40	38
Tensile Grab	MD	ASTM D 5034-09		lbs.	21	17
Grab Elongation	MD	ASTM D 5034-09		%	132	111
Tensile Grab	CD	ASTM D 5034-09		lbs.	18	14
Grab Elongation	CD	ASTM D 5034-09		%	137	111



**Sailrite Enterprises, Inc.**  
2390 East 100 South, Columbia City, IN 46725

**Phone** (800) 348-2769 / (260) 244-4647

**Fax** (260) 818-2005

**Email** [info@sailrite.com](mailto:info@sailrite.com)

**Sailrite.com**

© 2020 Sailrite Enterprises, Inc.